

KAWASAKI STEEL GIHO

Vol.2 (1970) No.4

On the Development of the Pelletizing Installation and Technics at Chiba Works

(Tsutomu Masuyama) (Hiroshi Takahashi) (Hachiro
Tsukamoto) (Takashi Oshima)

:

1953 11

1,000t/day

(1)

(2)

(2)

1,000t/day

0.8

Synopsis :

Started in October 1953, the pelletizing plant at Chiba Works now operates at the rate of 1,000t/day per furnace level after a number of improvements on the shaft furnace. The success is largely attributed to the following improvements; (1) Utilization of hot air (200-300) in the drying zone of the furnace, and (2) blowing in of cooling air into the cooling zone of the lower section of the furnace. Of these, the blowing in of cooling air

千葉製鉄所におけるペレット製造設備および 上位の改善法


Tsutomu Masuyama Hiroshi Takahashi
塙 本 八 郎 大 島 位 至******
Hachiro Tsukamoto Takashi Oshima

Synopsis:

Started in October 1953, the pelletizing plant at Chiba Works now operates at the rate of 1,000 t/day per furnace level after a number of improvements on the shaft furnace. The success is largely attributed to the following improvements;

- (1) Utilization of hot air (200~300°C) in the drying zone of the furnace, and
- (2) blowing in of cooling air into the cooling zone of the lower section of the furnace.


では 2,300 t を超える生産量を確保するにいたつ



来種々の改造をおこなっている。これらのうちおもに 1,000 t/day 炉の改造について述べる。

2・3・1 热風ダクト方式の採用

热風ダクト方式とは、焙焼炉に装入し



その結果前記の熱風ダクト設置による炉内温度の均一化がさらに促進され、過焼成によるブロックの発生はなくなり、冷







Table 2 Operational data of 1,000 t/day-furnace in September, 1969


Output (t/day)	1039
Fine product rate (%)	2.6
Working time (%)	92.5
Magnetic concentrate in pellet feed (%)	73.3

しく低下すること、さらにブロックを形成しやすくなる傾向があることを認めた。したがって、ペレット原料中の SiO_2 量

Grinding cake	4340
Green ball	2687
Moisture of green ball (%)	9.5

の製造を行なっていなか
った。そこで上記問題点
を解決するために、さら






10
5
0 \square Δ \circ SiO_2 6.2% \blacksquare \blacktriangle 2.9%

UD





熱衝撃による粉化が著しく減少した。

(2) 冷却空気の吹込みによって炉内温度分布が
均一となり、爐内粉化が少なくなった。またブ

トの製造は困難視されていたが、炉の数次の改
造により、爐基度 0.8 のペレットの製造が可能
となつた。

(3) メッシュコンベアの採用により排出コンベ
ア上の散水の必要がなくなり、ペレットの品質
が著しく向上した。
また焙焼炉の操業およびペレットの品質的な特
徴としては

この他、今後の計画としては、焙焼炉の大型化
(1,500t/day 程度)を予定しており、また操業的には
還元性状の改善などの観点より、MgO 添加ペレ
ットの製造およびベントナイトに代わる粘結剤の
工場試験を近々実施する予定である。最後に、石