

] 10 5r •

KAWASAKI STEEL GIHO

Vol.14 (1982) No.3

9>#Ni 5δ b(ç " Y | å © i Y » '5 MIG P K

Matching Ferritic Filler MIG Welding of 9% Ni Steel

7?,j M#è(Kazuo Agusa) ,#Ö G Ü(Masaaki Kosho) 0Y £ ¼(Noboru Nishiyama)

6J#ä í4{ (Akio Kamada) p5 • e (Yoshifumi Nakano)

O[" :

| u8®-(ò ç • á - Ö _ | •(ç " Y | å © i Y » MIG " i j b ó i • j > & x > ' t 9>
 Ni 5δ b '5 P K _4:#Y K>* P K5 " b*• Ø m € ö>* µ "\$x ö2A ^ } g %Ú o L f ö _ X
 8 Z1* m S) Y>* '5 P K b #Y i @ •+ ^ G \ @ Å ? _ ^ W S " } € S B Y +0[("U M
 •\ b \ > ~ [6 • (1) '5 P K5 " b*• Ø m € ö c>*9x Ni (Ô P K5 " | ~ M D €>*
 j P i ±4Š _ v m € c\$î#Ö K ^ 8 (2) ² P%T5 " > | g P K) E m b , G"l ö c>*5δ È b Q
 € _ [M • G \ ? }>*0¿0£0Á Å Š b , V F @ •+ [6 • (3) '5 P K5 " b * L f
 ö c>(ç " Y | å © i Y » _ ö Y C *4ß(ò i \ * © Ü ¥ å á - Ö b Q#Y _ | ~>*9x Ni (Ô P
 K5 " \ '½ b M D € S í t&g M (4) '5 P K4Š c>* M D € S%Ú o L f ö t w M •

Synopsis :

A technique for stabilizing pure argon shielded MIG arcs using rare earths-bearing electrode wires has been applied to the matching ferritic filler welding of 9%Ni steel. Investigations have been made on the hot crack susceptibility, mechanical properties and fracture toughness of weld metals. The results of the investigations summarized below have proved the practicability of the matching ferritic filler welding. (1) Hot crack resistivity of ferritic weld metals is far better than that of high-Ni-based weld metals, with no crack occurring even in weld craters. (2) Tensile properties of all-deposited metals and welded joints are equal to those of the base plates, with a rise in the allowable design stress value. (3) Ferritic weld metals obtained with pure argon shielded MIG arcs have excellent low-temperature toughness based on the reduction in silicon and oxygen contents. (4) Matching ferritic welds obtained with pure argon shielded MIG arcs have excellent fracture toughness.

(c)JFE Steel Corporation, 2003

Matching Ferritic Filler MIG Welding of 9% Ni Steel

阿草一男*

Kazuo Agusa

古生正昭**

Masaaki Kosho

西山昇*

Noboru Nishiyama

鎌田晃郎***

Akio Kamada

中野善文****

Yasuharu Nakano

Synopsis:

A technique for stabilizing pure argon shielded MIG arcs using rare earths-bearing electrode wires has been applied to the matching ferritic filler welding of 9%Ni steel. Investigations have been made on the

び163)を用いた場合のじん性も、550~600°Cの温度範囲において最高値を示したが、溶接金属中酸素量に対しては一律の相関を示さなくなり、シリコン量が高い場合には、低酸素化がじん性改善の手段とはなり得ないことがわかった。Fig. 2に、溶

して低シリコンのものを用い、シールドガスとして純アルゴンを用いることが必要となる。

Photo. 1に、溶接金属の光学顕微鏡組織に及ぼす熱処理温度の影響を示す。溶接のままの状態ではマルテンサイト主体の組織を呈し、この組織は




Photo. 2 Typical wire tip shape of rare earth-bearing wire during stable instantaneous short circuit transfer

スパッタの微細化やアンダカットの抑制が可能となる。

アーク電圧と溶接電流を広範囲に変化させてアーキ安定条件を求めたが、通常組成のワイヤでは




Fig. 4 Relationship of metal transfer modes to voltage/current conditions

トライン試験は、肉盛溶接した試験ビード表面をTIGアーキで溶融させた後、溶接部を冷却して

験条件は、電流と電圧を一定(280A, 26V)とし、法とともに、高Ni系溶接金属のその数分の1となる

溶接条件における割れ感受性を、MIG 法と共金溶接金属における割れ感受性を比較する。

~2.5mmの間で変化させ、1試験片当たり1ビードの溶接を行った。



4・2 試験結果および考察



トランスバレストレイン試験における付加重量


た。MIG法においてTIG法の約10倍の割れ長さとなるのは、溶接条件ならびに凝固形態の差によるものと考えられる。Table 6に、MIG法で試験した場合の凝固割れ感受性指数⁷⁾を示す。すべてにおいて共金溶接金属のほうがすぐれている。

Face









- 7) 仙田, 松田, 高野, 渡辺, 小林, 松板: Trans-Varestraint 試験法による溶接金属の凝固割れ感受性の研究 (1), 溶接学会誌, 41 (1972) 6, 113~127
- 8) 片山: 9%Ni鋼製LNG貯蔵タンクにおける溶接の自動化, 石川島播磨技報, 16 (1976) 3, 253~262
- 9) S. Minehisa, A. Nagai, Y. Shirane, and T. Nakata: "Automatic Welding of 9%Ni Steel," Hitachi Zosen Technical Rev., 39 (1978) 2, 140~146