

g f ® ¼t`
KAWASAKI STEEL GIHO
Vol. 32(2000) No.2

Å I j H Å Á o 590 MPa ½ÆSA440Ç : Q š ! & k ¥ ¼Ä . X h , O . ç }

Steel confirmed that it can ensure good mechanical property of pipes to which heat treatment is applied after receiving plastic deformation, and also obtain a good weld metal of the fabricated box section.

(c)JFE Steel Corporation, 2003

~ w / %o. C I > / 6 ¾° * fl 1 # .

高強度・高靱性 590 MPa 鋼 (SA440) を使用した
建築鉄骨の加工条件の究明*

川崎製鉄技報
32 (2000) 2, 139-143

Study of the Fabrication Method of 590 MPa Steel (SA440)
with High Tensile Strength and High Ductility

要旨

新しい高強度・高靱性の 590 MPa 鋼 (SA440 鋼) は焼入-二相

る。

2 SA440 鋼の特徴

Table 3 に高性能 590 MPa 鋼の要求性能を示す。

4.1.3 試験内容

- (1) 実際の管を造管する前に予備試験として、外径 700ϕ × 板厚 60mm に相当する曲率 ($R/D = 0.49$) の鋼板の予備試験

[The page contains approximately 25 lines of text that are almost entirely obscured by heavy horizontal black bars, likely due to scanning artifacts or redaction. Only a few faint characters and lines are visible.]

Table 9 Results of the Charpy V-notch tests

TP	Charpy V-notch	TP	Charpy V-notch	TP	Charpy V-notch
----	----------------	----	----------------	----	----------------

The table body is almost entirely obscured by heavy black redaction bars. Only a few faint horizontal lines are visible, suggesting the presence of multiple rows of data. The redaction covers the majority of the page's content area.